



DIAMOND POLYMERS, INC.

Injection Molding Grade

ABS 3500 ELG
Natural 1003

High Flow, Medium Impact
Low Gloss

PROPERTIES	ASTM METHOD	UNITS ENGLISH METRIC	
PHYSICAL			
Melt Flow Rate - Procedure A Condition G (200° C/5.0 kg) Condition I (230° C/3.8 kg)	D-1238	g/10 min g/10 min	-- 12.0
Specific Gravity	D-792		1.04
Mold Shrinkage	D-955	in/in cm/cm	0.004 - 0.007 0.004 - 0.007
Rockwell Hardness	D-785	R scale	104
IMPACT			
Izod Impact, notched 0.125", 23° C (73° F)	D-256	ft-lb/in J/m	2.5 133
FLEXURAL			
Flexural Modulus, tangent, chs 0.05 in/min	D-790	psi MPa	300,000 2,067
TENSILE			
Tensile Yield Strength, chs 2 in/min	D-638	psi MPa	6,000 41.3
THERMAL			
Heat Deflection Temperature 0.125" bar @ 1.8 Mpa (264 psi) Unannealed/Conditioned 48 hours @ 23° C (73° F)	D-648	°F °C	165 74
Vicat Softening Point, 0.125", 1Kg	D-1525	°F °C	215 102
FLAMMABILITY RATING			
Minimum Thickness 1.5mm / 0.0625in / 1/16" 2.5mm / 0.100in / 3/32" 3.0mm / 0.125in / 1/8"	UL 94		HB

EAP/04-18-07

The information contained herein is provided for general reference purposes only. Diamond Polymers Inc. makes no guarantee or warranty and does not assume liability with respect to the accuracy or completeness of the information presented, or the product results in any specific instance and hereby expressly disclaims any implied warranties of suitability or fitness for a particular purpose or any other warranties or representations whatsoever expressed or implied. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of patent.